

WBU 50 MATTE

PRODUCT CODE:

56% solids matte finish water based urethane

PRODUCT DESCRIPTION

WBU 50 Matte is a high solids, two-component water based aliphatic polyurethane. WBU 50 Matte has excellent hardness, abrasion resistance hot tire, and chemical resistance. WBU 50 Matte is low VOC and low odor with multiple uses.

BENEFITS/FEATURES

- ◆ Low viscosity allows for excellent substrate wetting and penetration.
- ◆ Provides superior resistance to many common chemicals, solvents and hot tire pick up.
- ◆ Excellent abrasion resistance that rivals many solvent based products.
- ◆ Matte finish and low odor make this ideal for many interior applications.
- ◆ VOC compliant for most areas in the United States and Canada.

RECOMMENDED APPLICATIONS

WBU 50 Matte is recommended for use in many interior applications where a low odor, matte finish, and abrasion resistant coating is required.

TECHNICAL INFORMATION

Solids.....	56 %	Re-Coat Time Window.....	10 - 14 hours
Pot Life.....	45 minutes	Dry Appearance.....	Clear and Matte Finish
Dry Time - Tack Free.....	5 - 6 hours	VOC Content.....	< 100 g/L mixed A&B
Dry Time - Foot Traffic.....	16 - 20 hours		
Dry Time - Heavy Traffic.....	4 - 7 days		
Application Temp.....	50°F - 80°F		

***Please note that low air and/or concrete temperatures and/or relative humidity may extend drying times. Follow recommended coverage rates for best results.

SPECIFICATIONS/COMPLIANCES

- Dried coating is USDA accepted
- Meets OTC, CARB, LADCO & SCAQMD VOC restrictions.

APPROXIMATE COVERAGE RATES

<u>Application Surface</u>	<u>First Coat</u>	<u>Optional Second Coat</u>
See back of this data sheet		

*Coverage rates vary depending upon surface porosity and texture, and application method. Excessive build up should be avoided.

SHELF LIFE

WBU 50 Matte has a shelf life of up to one year from manufacture date in it's original, sealed, unopened container.

PACKAGING

WBU 50 Matte is packaged in 3 gallon and 15 gallon kits.

THE STAIN STORE

223 W Nakoma Dr
San Antonio, TX 78216

HIGH PERFORMANCE COATINGS

WBU 50 MATTE

INSTRUCTIONS FOR USE

MOISTURE TESTING: Concrete floors, especially those not poured over a proper vapor barrier (plastic), are subject to possible moisture vapor transmission which may result in bubbling and/or failure of high performance coatings. Basic moisture testing can be performed by placing a 4' x 4' sheet of plastic on the concrete surface and securely taping it down on all edges. If after 24 hours the concrete is still dry below the plastic, the surface should be ready to coat. If moisture is present, the coating applicator should perform calcium chloride and relative humidity probe testing to determine if excessive levels of vapor emissions are present before applying any coatings.

SURFACE PREPARATION: The concrete surface must be deemed mechanically and structurally sound, thoroughly clean of debris and completely dry. Concrete must be fully cured a minimum of 28 days. It is recommended to prepare the concrete surface by mechanical means such as shot blasting or diamond grinding with 30 grit or coarser diamonds to achieve a CSP-2 to CSP-3 profile. If using in a thin mil system such as acid stain, dye & seal, 2 or less clear coats, etc., an 80 grit diamond may be acceptable to minimize visual scratches in the finish. Vacuum concrete surface several times until dust thoroughly removed. If applying over an existing, fully bonded coating that is outside its recommended recoat window, the surface should be sanded thoroughly with a 60-120 grit sanding screen until the surface is completely dulled with scratches. Vacuum dust thoroughly, rinse with clean water and remove excess water with a wet/dry vacuum or floor scrubber. Allow surface to dry completely prior to application of coating. Where applicable and with adequate ventilation, wipe the surface with acetone and a microfiber dust mop. **CAUTION:** Acetone is extremely flammable! If using acetone follow all safety precautions, make sure no pilot lights, open flames, sources of static electricity, sparks or extreme heat sources are present. Use recommended personal protection for acetone.

Substrate, air and material temperatures must be no less than 50°F and not exceed 80°F. If applied outside these limits the coating may not achieve adequate film formation and may have excessive air entrapment, bubbles, blushing or hazing. Please note that higher substrate, air and material temperatures as well as excessive humidity may speed the cure rate of this product. Cooler temperatures and lower humidity may slow the cure rate of this product.

FOR PERSONAL PROTECTION USE GLOVES, GOGGLES, RESPIRATOR AND OTHER NECESSARY PPE. REFER TO SDS PRIOR TO USE!

TINTING: Suggested as a clear top coat only. Tinting is not recommended. Color float and/or inconsistent color profile may leave an undesirable finish.

MIXING: If mixing less than a full kit, mix Part A and Part B separately with a stir stick, low speed mixer or vigorously shake containers prior to measuring out the smaller kit to ensure uniform distribution of all ingredients. In a clean mixing container, blend 2 Parts A and 1 Part B using a drill mixer for 2-3 minutes. Up to 10% clean water may be added AFTER blending Parts A and B to help reduce roller marks, orange peel, etc. Avoid creating a vortex in the material which could introduce air and/or moisture content to the mixture. Do not mix more than can be applied within the usable pot life time frame.

COVERAGE RATE:

First Coat - Direct to Concrete : 200 - 300 ft² per gallon*

Second Coat - Over Existing Coating : 250 - 350 ft² per gallon*

*Coverage rates may vary depending upon surface porosity, texture, application method and prior coating application. Excessive build up should be avoided.

APPLICATION: Using a brush and/or 3/8" nap shedless roller, dip and roll the mixed material from a roller pan. 18" rollers are recommended for any surface to speed up application time and reduce roller marks. Start by placing the wet roller at one corner of an approximate 4' x 4' square and roll the material at an angle to opposite corner applying no pressure to the roller. Spread the material across only that square and immediately back-roll to even out material and roller lines. Adjust the size of your square as needed based on the amount of material being applied with the roller. After finishing the square, move on to the next square using the same technique. While applying keep a wet edge to prevent roller marks. It is recommended to work in sections usually using control joints as dividers to ensure proper application results. Apply the mixed material within the usable pot life time frame. If the material becomes thick while applying and sticking to the roller, stop applying and discard the mixed material. At this point it has reached the end of the usable pot life. Do not allow to puddle! Use a brush to remove excess coating in joints. An airless or HVLP sprayer may also be used.

RECOATING: If possible, recoat within the suggested recoat window located on page 1. Apply additional coats in the same manner as the first coat. Note that higher substrate, air and material temperatures as well as excessive humidity may greatly reduce the acceptable recoat window of this product. When working in higher temperatures, always recoat as early in the recoat window as possible to avoid failure between coats. If recoating outside the suggested recoat window (see page 1) or beyond 24 hours, sand using a 60-120 grit sanding screen to ensure adequate adhesion between coats. Vacuum dust thoroughly, rinse with clean water and remove excess water with a wet/dry vacuum or floor scrubber. Allow surface to dry completely prior to application of coating. Where applicable and with adequate ventilation, wipe the surface with acetone and a microfiber dust mop. **CAUTION:** Acetone is extremely flammable! If using acetone follow all safety precautions, make sure no pilot lights, open flames, sources of static electricity, sparks or extreme heat sources are present. Use recommended personal protection for acetone.

PLEASE NOTE: Applying material outside the suggested parameters may result in product failure. It is always recommended to test the product in a small, inconspicuous area (on the same concrete substrate) for desired results prior to application. Coverage rates may vary for all coatings and substrates depending on porosity, density, texture etc. When applying, adhere to suggested coverage rates. Applying too thin of a coating may cause inadequate film formation, limited performance expectations and/or undesirable finish. Applying too thick may result to bubbling, hazing, etc. **DO NOT USE ON BRICK.**

COF WARNING: OSHA and the American Disabilities Act (ADA) have now set enforceable standards for slip-resistance on pedestrian surfaces. The current coefficient of friction required by ADA is .6 on level surfaces and .8 on ramps. The manufacturer recommends the use of slip-resistant aggregate in all coatings or flooring systems that may be exposed to wet, oily or greasy conditions. It is the contractor and end users' responsibility to provide a flooring system that meets current safety standards. The manufacturer nor its sales agents will be responsible for injury incurred in a slip and fall accident.

CLEAN-UP

Use MEK or Acetone. Dispose of containers in accordance with local and federal regulations.

PRODUCT REMOVAL

Dried, cured coating may be removed with a commercial stripper or by using a diamond grinding method, sandblasting method or similar mechanical action.

PRECAUTIONS AND LIMITATIONS

- ◆ This product will freeze during storage. Store at temperatures above 40°F.
- ◆ All HVAC ventilation ducts should be somehow blocked prior to application so solvent fumes are not distributed.
- ◆ If using indoor, use proper ventilation while applying and for hours after application to ensure fumes are removed.
- ◆ It is not recommended to apply product over carpet, tile, or other types of floor adhesives.
- ◆ This product performs best when applied as one or two medium-light coats, not one heavy coat.
- ◆ Please be aware that this product when cured may be slippery when wet. An anti-slip additive, such as Surf-Grip, can be added to reduce slip hazards.
- ◆ All new concrete must be cured for at least 28 days prior to application.
- ◆ It is not recommended to thin product. Improper thinning may cause coating to delaminate in a short time frame and other performance issues.
- ◆ This product may darken the surface of many new and existing concrete slabs. Test prior to use.
- ◆ Physical properties listed on this technical data sheet are typical values not specifications.

SPECIAL NOTES

Please consult Material Safety Data Sheet (MSDS) and read Warranty information prior to use. This information can be requested by contacting customer service at 210-340-4627.

THE STAIN STORE

223 W Nakoma Dr
San Antonio, TX 78216